

Water Repellents And Curing Aids

Technical Data Bulletin



Super Stucco Primer/Sealer™ Concentrate with Micro-Lok™ 100% PENETRATING WATER REPELLENT

PRODUCT DESCRIPTION

Rainguard *SUPER STUCCO PRIMER/SEALER* Concentrate with *MICRO-LOK* Clear Water Repellent is a water based, modified polysilane/siloxane repellent composed of high quality chemical solids, blended to create a clear, deep penetrating and non-film forming chemically reactive masonry water repellent that contains no silicone oils, paraffin wax or urethanes. This product will not re-emulsify.

MICRO-LOK creates a micro-molecular chemical and mechanical bond between the water-repellent chemicals and the stucco material. *SUPER STUCCO PRIMER/SEALER* Concentrate penetrates deep into dense masonry surfaces to provide long lasting and virtually indestructible water repellent protection that is not affected by weather or sunlight. Helps prevent spalling and cracking caused by freeze thaw cycles. Helps prevent chloride ion intrusion and efflorescence.

SUPER STUCCO PRIMER/SEALER Concentrate must be diluted with 14 parts clean water prior to application.

PRODUCT FEATURES

1. Exclusive *MICRO-LOK* formulation
2. Mold and Mildew Inhibitor
3. Protection not affected by weathering or UV light
4. Single coat application
5. V.O.C. compliant
6. Contains no known carcinogens

Warranty Period: Five Years

CSI Reference: Division 7

Part Numbers: USA International
1 Gallon CR-0300 CR-0300-CA

RECOMMENDED USES:

- Primer for stucco
- Sealer for stucco
- Concrete
- EFIS or cement plaster
- May be used on composite construction with a variety of substrates.
- An excellent primer for paint applications

COVERAGE RATES (THEORETICAL):

Dense Surfaces

<u>One Coat</u>	<u>Sq Ft/ Gallon</u>
EFIS	75-100
Clay Tile	100-150
Cement Plaster	100-150
Clay Block	100-150
Cast Concrete	150-175
Stucco	150-200

Special Considerations:

- Use of fluted or scored block or raked joints will increase surface areas by 20%-30% or more and decrease coverage rates. Allow for this increased surface area when determining material requirements.
- Extremely porous surfaces may require multiple coats.

Manufactured by:

Rainguard International
1079 Culpepper Drive, Conyers GA 30094

1-866-989-5159

949-675-3450 Fax

info@rainguard.com

www.rainguard.com

© Weatherman Products, Inc. Version 06.09

PRECAUTIONS & LIMITATIONS

All surfaces to be coated shall be clean of any dirt and grime, efflorescence, lime run, form oils and release agents, grease, mud, excess mortar and mold and mildew, etc. All cracks shall be pointed or caulked. All voids, bee-holes, masonry surface defects and openings such as conduits, pipes, drains, door frames, vents, air conditioner openings, electrical openings, control joints or any dissimilar materials shall be repaired using urethane or other approved patching. May be applied to fresh concrete/stucco after 48 hours.

DILUTE THIS MATERIAL USING CLEAN WATER AT A RATIO OF 14 PARTS WATER TO 1 PART CONCENTRATE.

Do not apply to surfaces if moisture content is greater than 15% as measured with an electronic moisture meter. Do not apply materials in climates where freezing temperatures have existed prior to application, allow adequate time for surfaces to thaw. Establish that air, surface and material temperatures are above 35°F (2°C) and at least 5°F above the dew point prior to application. Do not apply at temperatures below 35°F or when temperatures are expected to drop below 35°F within 48 hours of application. Do not apply if rain, snow or lower temperatures are expected within 48 hours. Do not apply if relative humidity is greater than 80%.

Use material in a well ventilated area. Protect the work of other trades. Protect shrubbery and other plants with drop cloths. Protect automobiles and all other areas not to be coated from overspray. Remove overspray from any windows, automobiles, metal etc. as soon as possible should it occur. To prevent permanent staining, clean spills or leaks in a timely manner.

Store materials in a well-protected area between 45° and 90°F. Avoid freezing temperatures, direct sunlight and moisture. Keep away from heat sources

TEST PANEL:

Always apply material to a mock wall or test panel, test wall or actual surface area to determine acceptable color, surface porosity, application rates and methods before starting general application.

FOLLOW THESE SIMPLE STEPS

1. SUPER STUCCO PRIMER/SEALER should be applied using low-pressure airless spray equipment.
2. Avoid atomizing material by using a spray tip size of .060 to .110. Spray head should be held 8 to 12 inches from the surface so that the flood coat runs down the wall approximately 6-12 inches below the point of application.



Manufactured by:

Rainguard International

1079 Culpepper Drive, Conyers GA 30094

1-866-989-5159

949-675-3450 Fax

info@rainguard.com

www.rainguard.com

© Weatherman Products, Inc. Version 06.09

3. Avoid application in windy weather.
4. Trigger gun off at the end of each pass to avoid using excessive materials. Stop all applications only at corners, joints, seams or edges.
5. **Multiple coats may be applied.**

TECHNICAL DATA

Material Type	Modified Polysilane/Siloxane
Active Solids Content	Approximately 11% after Dilution
Color of Material	Clear to Slightly Cloudy
Odor	Slight Ammonia Odor
V.O.C.	<15 g/L V.O.C. Compliant
Flash Point	Non-Flammable
pH Value	Approximately 12.5
Viscosity	9.6 Seconds No. 4 Ford Cup
Weight	Approximately 8.5 lbs./gal.
Surface Dry/Recoat	Approx 1 Hour
Full Chemical Cure	24 to 36 Hours

TEST DATA

Wind Driven Rain	ASTM E-514-86	96.2% Leak Red
Water Pen Fed Spec	SS-W-110C	75% Min Req
		96.8% Leak Red Chloride Ion Intr Salt
Pounding NCHRP No. 244		Allowed 25% - Obtained 13.0%
Water Abs CMU ASTM C140-75		89% Effective
Water Vapor Trans ASTM D-1653		100% Vapor Perm
Water Repellency ASTM C67-80A		97% Effective
Weathering ASTM G-53		2500 Hours – No Change

LIMITED WARRANTY PROCEDURES/INFORMATION

The information contained herein is offered in good faith and is believed to be accurate. To be eligible for a Rainguard Warranty the following must occur:

1. A site visit must be conducted by an employee or agent of Rainguard and a Field Inspection Report completed.
2. A Warranty Application must be completed fully by the applicator.
3. Field Inspection Report, Warranty Application and a copy of the distributor's invoice must be submitted to and approved by Rainguard.

This material is only warranted when applied in accordance with the manufacturers guidelines and warranty procedures. Without adherence to these specific guidelines, no expressed or implied warranty of this product is given. Please contact Rainguard for additional information.

